

Radiation Products Design Inc

SAFETY DATA SHEET

RPD INFORMATION

- Address 5218 Barthel Industrial Drive Albertville, MN 55301
- Website www.rpdinc.com
- Email sales@rpdinc.com
- Phone 763-497-2071 or 800-497-2071
- **Fax** 763-497-2295

RAW MATERIAL INFORMATION

ACRYLITE® FF Acrylic Sheet

1. Chemical Product and Company Identification

ACRYLITE[®] FF Acrylic Sheet

Supplier: A & C Plastics, Inc. 6135 Northdale Houston, TX 77087-5095

Product Information Number1-207-490-424224 Hour Emergency Number, CHEMTREC1-800-424-9300

® is a registered trademark

Product Use: building glazing, light advertising, furniture, trade-fair booth design, displays, decoration, Industrial Use

2. Composition/Information on Ingredients

This material is classified as not hazardous under OSHA regulations.

Ingredients	CAS Reg. No.	Weight %
acrylic copolymer	trade secret	100

NJTSR # 56705700001-6897 P

See Section 8, Exposure Controls/Personal Protection

3. Hazards Identification

Emergency Overview

Color:colorless or coloredAppearance:solid in various formsOdor:odorless

Under normal conditions of use, this product is not expected to create any unusual industrial hazards.

Primary Routes of Exposure Eye contact (if exposed to chips)

Potential Health Effects

Inhalation No hazard expected in normal use.

Eye Contact

No hazard expected in normal use. Material can cause the following: - mechanical irritation



Skin Contact Material can cause the following: - cuts (when using cut sheets) Ingestion

No hazard expected in normal use.

Potential Environmental Effects See SECTION 12, Ecological Information

4. First Aid Measures

First Aid Procedures

Inhalation

No specific treatment is necessary since this material is not likely to be hazardous by inhalation.

Eye Contact

If mechanical irritation occurs flush eyes thoroughly with a large amount of water, consult a physician if irritation persists. (possible during machining processes)

Skin Contact

No specific treatment is necessary since this material is not likely to be hazardous.

Ingestion

Ingestion is not considered a potential route of exposure.

5. Fire-Fighting Measures

Flash point	> 250 °C (ASTM D1929-68) > 482 °F(ASTM D1929-68)
Autoignition Temperature	> 400 °C (ASTM D1929-68) > 752 °F(ASTM D1929-68)
Lower explosion limit	not applicable
Upper explosion limit	not applicable
OSHA Flammability Classification	none
Other Flammable Properties Use water spray to cool containers ex Extinguishing Media	posed to fire.

Use the following extinguishing media when fighting fires involving this material:

water spray - foam - dry chemical - carbon dioxide

Fire Fighting Procedures

As in any fire, wear self-contained breathing apparatus pressure-demand, MSHA/NIOSH (approved or equivalent) and full protective gear.



6. Accidental Release Measures

Procedures

Collect material and place in a disposal container. Obey relevant local, state, provincial and federal laws and regulations.

See Material Safety Data Sheet section 8, Exposure Controls/Personal Protection.

7. Handling and Storage

Handling

During thermal processing and/or machining local exhaust ventilation at processing machines is necessary.

Storage

Storage: dry.

8. Exposure Controls/Personal Protection

Exposure Limit Information

ACRYLIC COPOLYMER

trade secret

No Occupational Exposure Values established (ACGIH, OSHA, Canada and Mexico).

Engineering Controls (Ventilation)

If use operations generate dust, use adequate ventilation.

Respiratory Protection

A respiratory protection program meeting OS HA 1910.134 and ANSI Z88.2 requirements must be followed whenever workplace conditions warrant a respirator's use.

Eye Protection

goggles for machining operations

Hand Protection

protective gloves against mechanical risks

Other Protective Equipment

To identify additional Personal Protective Equipment (PPE) requirements, it is recommended that a hazard assessment in accordance with the OSHA PPE Standard (29CFR1910.132) be conducted before using this product.

9. Physical and Chemical Properties

Appearance	colorless or colored
Physical state	solid in various forms
Odor	odorless
Flash point	> 250 °C (ASTM D1929-68)
	> 482 °F (ASTM D1929-68)
pH-value	not applicable



Pg. 3 pH-va

Viscosity (dynamic)	not applicable
Specific gravity (water = 1)	1.19 g/cm3 at 20 °C / 68 °F
Vapor density (air $=$ 1)	not applicable
Vapor pressure	not applicable
Softening Temperature	approx. 102 °C / 216 °F
Boiling Temperature	not applicable
Solubility in water	insoluble
n-Octanol/water partition coefficient	not applicable
Evaporation rate	not applicable
Odor threshold	not available
Further information	none
See Section 5, Fire Fighting	y Measures

10. Stability and Reactivity

Stability This product is stable under normal storage conditions. Conditions To Avoid This material is considered stable. Incompatibility With Other Materials Oxidizing agents. No known incompatibility with other materials. Hazardous Decomposition Products In case of thermal decomposition, combustible vapours are formed, which are irritating to eyes and respiratory system, mainly consisting of: methyl methacrylate Hazardous Polymerization

Product will not undergo polymerization.

11. Toxicological Information

Further Information on Toxicology

The product has not been tested toxicologically. When handled and used as directed the product will not cause hazardous effects to health according to studies on similar products and practical experience.

12. Ecological Information

Information on Elimination (Persistence and Degradability)

Ecotoxicological Effect

Further Information on Ecology

The product has not been tested eco toxicologically. On the basis of the products consistency as well as its low water solubility a bio availability is unlikely.Studies on products with similar composition confirm this assumption.

13. Disposal Considerations

Procedures

Waste must be disposed of in accordance with federal, state and local regulations. Incineration is the preferred method. A & C Plastics encourages the recycle, recovery and reuse of materials, where permitted, as an alternate to disposal as a waste.

14. Transport Information

Further information Not subject to the regulations on dangerous goods.

15. Regulatory Information

INVENTORY INFORMATION	
EINECS (EU)	listed or exempted
TSCA (USA)	listed or exempted
DSL (CDN)	listed or exempted

US FEDERAL REGULATORY INFORMATION

Component / CASRN	TPQ [lbs]	CERCLA RQ [lbs] (40CFR302.4)	SARA 302 List of EHS	SARA 313 (40CFR372)	TSCA 12b
NONE					

COMPONENT CLASSIFICATION UNDER CLEAN AIR ACT SECTION 112

Component / CASRN	Weight %	HAP	EHAP

NONE

PRODUCT CLASSIFICATION UNDER SECTION 311/312 OF SARA (40CFR370)

NONE

US STATE REGULATORY INFORMATION

Component / CASRN	New Jersey RTK	Pennsylvania RTK	Massachusetts RTK	California Proposition 65 Cancer	California Proposition 65 Reproductive
acrylic polymer / trade secret	NO	NO	NO	NO	NO

This product contains (a) chemical(s) known to the State of California to cause cancer and birth defects or other reproductive harm.



This product has been classified in accordance with the hazard criteria of the Controlled Products Regulation and the MSDS contains all information required by the Controlled Products Regulations.

This is a non-controlled product. WHMIS: NO

Component / CASRN	NPRI

NONE

16. Other Information

	Health	Flammability	Physical Hazard
HMIS-Ratings	0	1	0
NFPA-Ratings	0	1	0
	HMIS Hazard Ratings	NFPA Haza	rd Ratings
	 4 = severe 3 = serious 2 = moderate 1 = slight 0 = minimal N = no rating for powders * = chronic health hazard 	4 = extreme 3 = high 2 = moderate 1 = slight 0 = insignificant N = no rating for powders	

This MSDS was prepared in accordance with ANSI Z400.1-1998.

Places marked by || have been amended from the last version.

This information and all technical and other advice are based on A & C Plastics, Inc. present knowledge and experience. However, A & C Plastics, Inc. assuumes no liability for such information or advice, including the extent to which such information or advice may relate to third party intellectual property rights. A & C Plastics, Inc. reserves the

right to make any changes to information or advice at any time, without prior or subsequent notice. A & C Plastics, Inc. DISCLAIMS ALL REPRESENTATIONS AND WARRANTIES, WHETHER EXPRESS OR IMPLIED, AND SHALL HAVE NO LIABILITY FOR, MERCHANTABILITY OF THE PRODUCT OR ITS FITNESS FOR A PARTICULAR PURPOSE (EVEN IF A & C Plastics, Inc. IS AWARE OF SUCH PURPOSE), OR OTHERWISE. A & C Plastics, Inc. SHALL NOT BE RESPONSIBLE FOR CONSEQUENTIAL, INDIRECT OR INCIDENTAL DAMAGES

(INCLUDING LOSS OF PROFITS) OF ANY KIND. It is the customer's sole responsibility to arrange for inspection and testing of all products by qualified experts. Reference to trade names used by other companies is neither a recommendation nor an endorsement of the corresponding product, and does not imply that similar products could not be used.